



INSTALLATION GUIDELINES

RASCOTight Hydrophilic Paste

GENERAL

The hydrophilic paste shall be allowed to cure prior to concreting. Depending on temperature and bead size, this may take between approx. 18 and 24 hours. During this period and prior to casting, the hydrophilic paste shall not be allowed to come into contact with water. The cartridges have a double bottom that has to be removed prior to use. The cartridge opening has to be pierced before screwing on the pointed nozzle.


PERSONAL PROTECTIVE EQUIPMENT

- Wear suitable protective gloves and goggles



INCORPORATION

- Always install 3 rings of hydrophilic paste
- Minimum concrete cover: 10 cm



FIXING

- Cut off tip of pointed nozzle (opening approx. 1 cm)
- Press out material
- Hold nozzle tip close to base to achieve required pressure during application



JOINTS

- Butt or lap joint to achieve continuous bead



LEGAL NOTICE: The information provided on the use and application of our products in this technical data sheet is based on the present state of our knowledge. The customer shall bear sole responsibility for the proper specification, application and use of the products in line with the intended purpose, project-specific conditions and external actions. The most recent technical data sheet shall apply. The current technical data sheets are available at www.rascor.com. Our General Terms of Business shall form an integral part of this technical data sheet.

Rascor International Ltd.
Gewerbestrasse 4
CH-8162 Steinmaur / Switzerland
Phone: +41 (0)44 857 11 11
Fax: +41 (0)44 857 11 00
www.rascor.com