



INSTALLATION GUIDELINES

RASCOTight QVE 20|03 SK

GENERAL

Good adhesion on non cementitious surfaces. The surface has to be free of fat and dust. To minimize the risk of water infiltration round the hydrophilic strip, we recommend the incorporation of two rings of hydrophilic strip in all cases. Spalling failure (due to swelling pressure) can be prevented by provision for a minimum concrete cover of 10 cm on all sides. Strip that has swollen by over 20% shall not be cast in.

PERSONAL PROTECTIVE EQUIPMENT

- Wear suitable protective gloves and goggles

INCORPORATION (GROUND SLABS, SUSPENDED SLABS, WALLS)

- Always incorporate two rings of hydrophilic strip
- Minimum concrete cover: 10 cm

FIXING

- Selfadhesive
- Fit tightly to base with no voids under strip
- do not twist when it gets layed

JOINTS

- Lap strip at side (without gap) by approx. 5 - 7 cm
- Or butt ends of strip (without gap)

